

इंटरनेट

मानक

Disclosure to Promote the Right To Information

Whereas the Parliament of India has set out to provide a practical regime of right to information for citizens to secure access to information under the control of public authorities, in order to promote transparency and accountability in the working of every public authority, and whereas the attached publication of the Bureau of Indian Standards is of particular interest to the public, particularly disadvantaged communities and those engaged in the pursuit of education and knowledge, the attached public safety standard is made available to promote the timely dissemination of this information in an accurate manner to the public.

“जानने का अधिकार, जीने का अधिकार”

Mazdoor Kisan Shakti Sangathan

“The Right to Information, The Right to Live”

“पुराने को छोड़ नये के तरफ”

Jawaharlal Nehru

“Step Out From the Old to the New”

IS 4161 (1967): Nessler cylinders [CHD 10: Glassware]



“ज्ञान से एक नये भारत का निर्माण”

Satyanarayan Gangaram Pitroda

“Invent a New India Using Knowledge”



“ज्ञान एक ऐसा खजाना है जो कभी चुराया नहीं जा सकता है”

Bhartrhari—Nitiśatakam

“Knowledge is such a treasure which cannot be stolen”

BLANK PAGE



IS : 4161 - 1967

REAFFIRMED 2006

Indian Standard
**SPECIFICATION FOR
NESSLER CYLINDERS**

UDC 542.3:531.73



© *Copyright* 1967

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 1

Gr. 2

August 1967

AMENDMENT NO. 2 JULY 2007
TO
IS 4161 : 1967 SPECIFICATION FOR
NESSLER CYLINDERS

(Page 4, clause 4.5) — Substitute the following for the existing clause:

'4.5 Limit of Alkalinity — When graded according to the method prescribed in IS 2303 (Part 1/Sec 1): 1994*, it shall conform to Class HGB 1 of the glass.'

(Page 4, footnote marked *) — Substitute the following for the existing:

*Grading glass for alkalinity : Part 1 Hydrolytic resistance, Section 1 Hydrolytic resistance of glass grains at 98°C - Method of test and classification (*first revision*).'

(Page 4, clause 5.1.1) — Substitute the following for the existing clause:

'5.1.1 BIS Certification Mark

The Nessler cylinders may also be marked with the Standard Mark.

5.1.1.1 The use of the Standard Mark is governed by the provisions of *Bureau of Indian Standards Act*, 1986 and the Rules and Regulations made thereunder. The details of conditions under which the licence for the use of Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.'

(CHD 10)

AMENDMENT NO. 1 NOVEMBER 1967

TO

IS : 4161-1967 SPECIFICATION FOR
NESSLER CYLINDERS

Alterations

(*Page 1, composition of CDC 33 : 1, left-hand column*) — Substitute '*Convener*' for '*Chairman*'.

(*Page 8, fifth line from top, right-hand column*) — Substitute '*National Chemical Laboratory (CSIR), Poona*' for '*National Physical Laboratory (CSIR), Poona*'.

(*Page 8, advertisement text on Laboratory Glassware, under column IS:)* — Substitute '*915*' for '*1915*'.

(CDC 33)

Printed at Standard Printing Work, New Delhi-1, India

Indian Standard

SPECIFICATION FOR NESSLER CYLINDERS

Laboratory Glassware and Related Apparatus Sectional Committee, CDC 33

Chairman

DR S. R. LELE

Representing

Borosil Glass Works Ltd, Bombay

Members

SHRI K. L. BANERJEE

DR N. K. DUTTA

SHRI Y. S. NIMBKAR (*Alternate*)

DR P. S. GILL

National Test House, Calcutta

Haffkine Institute, Bombay

Central Scientific Instruments Organization (CSIR),
ChandigarhSHRI AJIT SINGH (*Alternate*)

SHRI HARI DATTA

SHRI S. R. KHANNA

The Ganga Glass Works Private Ltd, Balawali
Directorate General of Technical Development
(Ministry of Supply, Technical Development
and Materials Planning)

DR S. KUMAR

Central Glass & Ceramic Research Institute
(CSIR), Calcutta

DR S. C. NIYOGI

SHRI PREM PRAKASH

SHRI K. V. RAMACHANDRAN

PROF V. RAMAKRISHNA

SHRI N. RANGASWAMY

SHRI D. C. ROY

SHRI A. SANKARANARAYANAN

SHRI D. J. RAO (*Alternate*)

Scientific Indian Glass Co Ltd, Calcutta

National Physical Laboratory (CSIR) New Delhi

Ministry of Defence (R & D)

Indian Institute of Technology, New Delhi

Glaxo Laboratories (India) Pvt Ltd, Bombay

National Instruments Ltd, Calcutta

Toshniwal Bros Private Ltd, Bombay

SHRI D. N. SEN

DR H. A. SHAH

DR P. G. TULPULE

SHRI P. C. VARSHNEI

SHRI P. P. CHANDRA (*Alternate*)

DR SADGOPAL,

Director (Chem)

National Chemical Laboratory (CSIR), Poona
Development Commissioner, Small Scale Industries
Indian Council of Medical Research, New Delhi
Seraikella Glass Works Pvt Ltd, KandraDirector General, ISI (*Ex-officio Member*)*Secretaries*

SHRI S. K. MATHUR

Deputy Director (Chem), ISI

SHRI G. P. SARASWAT

Assistant Director (Chem), ISI

Volumetric Glassware Subcommittee, CDC 33: 1

Chairman

SHRI PREM PRAKASH

National Physical Laboratory, New Delhi

(*Continued on page 8*)

INDIAN STANDARDS INSTITUTION
MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG
NEW DELHI 1

Indian Standard

SPECIFICATION FOR NESSLER CYLINDERS

0. FOREWORD

0.1 This Indian Standard was adopted by the Indian Standards Institution on 13 February 1967, after the draft finalized by the Laboratory Glassware and Related Apparatus Sectional Committee had been approved by the Chemical Division Council.

0.2 This standard covers Nessler cylinders normally used in scientific and industrial laboratories. Nessler cylinders are suitable for use in laboratories for comparing the colour of lightly coloured liquids.

0.3 In the preparation of this standard, assistance has been derived from B.S. 612 : 1952 'Nessler cylinders'.

0.4 For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS : 2-1960*. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

1. SCOPE

1.1 This standard prescribes the requirements and methods of test for Nessler cylinders used in laboratories for comparing the colour of light coloured liquids.

2. TERMINOLOGY

2.1 For the purpose of this standard, the definitions given in IS : 1382-1961†, in addition to the following, shall apply.

2.1.1 Capacity — The volume of water at 27°C in millilitres contained in the cylinder at 27°C when filled to the graduation line indicating nominal capacity, the lowest point of the meniscus being in the horizontal plane conforming to the top edge of the graduation line, with the cylinder in a vertical position.

*Rules for rounding off numerical values (*revised*).

†Glossary of terms relating to glass industry.

3. NOMINAL CAPACITY

3.1 The Nessler cylinders shall be of the following two capacities:

- a) 50 ml, and
- b) 100 ml.

3.2 Tolerance on Nominal Capacity — The maximum error in capacity for 50 ml cylinder shall not exceed ± 0.4 ml. The maximum error in case of 100 ml cylinder shall not exceed ± 0.8 ml at either of the graduation lines and the difference between errors at the 50 ml and 100 ml lines shall not exceed 0.8 ml.

4. REQUIREMENTS

4.1 Material and Workmanship

4.1.1 The cylinders shall be made of transparent glass as free as possible from strains and visible defects. They shall be well annealed.

4.1.2 The glass used shall be sufficiently free from colour to render it suitable for the colorimetric observations.

4.2 Construction and Finish

4.2.1 The cylinders shall be either mouth blown or made from glass tubing of as uniform a bore as possible. Each cylinder shall be finished at the top with a smooth fire-polished edge which may be strengthened by a slight beading, if desired. A small pouring lip shall be provided so that the liquid does not cling to the sides of the cylinder while pouring.

4.2.2 The base of the cylinder shall be flat and polished on the outside and shall be such that the cylinder shall stand vertically on a level surface without rocking. On the inside, the junction between the walls and the base shall be such that the inside of the base is parallel to the outside over largest practicable area.

4.2.3 When the cylinder is made from glass tubing the base shall either be formed from the tubing of which the body is made or shall be a glass disc permanently fused to the tube in a manner which precludes the possibility of liquid penetrating into the joint.

4.3 Dimensions — Nessler cylinders shall conform to the dimensions specified in Table 1.

NOTE — The tolerances on the heights to the graduation lines are adequate to allow for normal variations in manufacture. More stringent tolerances are not practicable. It is not possible, however, to use side by side Nessler cylinders differing from each other in height of graduation line by more than about 1 mm. Consequently in fulfilling any particular order, manufacturers or suppliers are expected to select from their stock, cylinders which agree satisfactorily with each other in height of graduation mark.

TABLE 1 DIMENSIONS OF NESSLER CYLINDERS

(Clause 4.3)

SL No.	DETAILS	NOMINAL CAPACITY	
		50 ml (3) mm	100 ml (4) mm
(1)	(2)		
i)	Overall height	150 ± 2	180 ± 2
ii)	External height to 50 ml mark	117 ± 7	—
iii)	External height to 100 ml mark	—	137 ± 8
iv)	Thickness of wall	1.0 to 1.5	1.2 to 1.8
v)	Thickness of base	1.5 to 3.0	1.5 to 3.0

4.4 Graduation Lines and Numbering

4.4.1 The cylinders of nominal capacity 50 ml shall have a graduation line corresponding to 50 ml and the cylinder of nominal capacity 100 ml shall have graduation lines corresponding to 50 ml and 100 ml.

4.4.2 The graduation lines shall be clean permanent lines of uniform thickness not exceeding 0.3 mm lying in planes at right angles to the axis of the cylinder and horizontal when the cylinder is standing on a level surface. Each graduation line shall be carried completely round the cylinder and appropriately numbered as shown in Fig. 1.

4.5 Limit of Alkalinity — When graded according to the method prescribed in IS : 2303-1963* it shall conform to Type 1 of the glass.

5. MARKING AND PACKING


5.1 Marking — The following inscriptions shall be permanently and legibly marked on the Nessler cylinders:

- Nominal capacity followed by the abbreviation 'ml';
- The abbreviation '27°C' to indicate the standard temperature at which it is calibrated; and
- Maker's name or recognized trade-mark, if any.

5.1.1 The Nessler cylinders may also be marked with the ISI Certification Mark.

NOTE — The use of the ISI Certification Mark is governed by the provisions of the Indian Standards Institution (Certification Marks) Act, and the Rules and Regulations made thereunder. Presence of this mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard, under a well-defined system of inspection, testing and quality control during production. This system, which is devised and supervised by ISI and operated by the producer, has the further safeguard that the products as actually marketed are continuously checked by ISI for conformity to the standard. Details of conditions, under which a licence for the use of the ISI Certification Mark may be granted to manufacturers or processors, may be obtained from the Indian Standards Institution.

*Method of grading glass for alkalinity.



All dimensions in millimetres.

FIG. 1 NESSLER CYLINDERS

5.2 Packing — Nessler cylinders shall be packed as agreed to between the purchaser and the supplier.

6. SAMPLING

6.1 Representative samples of the material shall be drawn and adjudged as prescribed in Appendix A.

APPENDIX A

(Clause 6.1)

SAMPLING OF NESSLER CYLINDERS

A-1. SCALE OF SAMPLING

A-1.1 Lot — In a single consignment all the Nessler cylinders coming from the same manufacturer and belonging to the same capacity shall constitute a lot.

A-1.2 Samples shall be taken from each lot separately for ascertaining the conformity of the cylinders to the requirements of this specification.

A-1.3 Test Samples — When the lot contains more than 42 items, only 42 items shall be selected at random from the lot. These 42 items shall be the test samples. When, however, the lot contains 42 or less than 42 items, all the items in the lot shall be treated as test samples.

A-1.3.1 In order to ensure randomness of selection of items from a lot, random number tables shall be used. In case the random number tables are not available, the following procedure may be adopted:

Starting from any item, count them as 1, 2, 3, etc, up to r and so on in one order; every r th item thus counted, shall be chosen where r is the integral part of $N/42$, N being the total number of items in the lot.

A-2. NUMBER OF TESTS AND CRITERIA FOR CONFORMITY

A-2.1 Alkalinity Test — Take two items at random out of the test samples selected according to A-1.3. Subject them to the alkalinity test in accordance with 4.3.

A-2.1.1 If both the items pass the alkalinity test, the remaining test samples shall be subjected to further tests for all other requirements; otherwise the lot shall be rejected without further testing.

A-2.2 Requirements Other than Alkalinity Test — For this purpose the procedure shall be as given in the following clauses.

A-2.2.1 Defective — A test sample failing in one or more of these requirements shall be called defective.

A-2.2.2 In case the test samples remaining after the alkalinity test are less than 40, all of them shall be tested for these requirements.

A-2.2.2.1 If the samples tested for these requirements are 20 or less, no defective shall be permitted; if however, the number of items tested is between 21 and 39, one defective shall be permitted.

A-2.2.3 In case the test samples remaining after the alkalinity test are 40, the procedure shall be according to **A-2.2.4** and Table 2.

TABLE 2 CRITERION FOR CONFORMITY AT DIFFERENT STAGES IN TESTING

STAGE	SAMPLE SIZE	CUMULATIVE SAMPLE		
		Size	Acceptance No.	Rejection No.
(1)	(2)	(3)	(4)	(5)
First	8	8	*	2
Second	8	16	0	2
Third	8	24	1	3
Fourth	8	32	2	4
Fifth	8	40	3	4

*Acceptance not permitted at this stage.

A-2.2.4 First Stage — In the first stage take 8 items at random from the 40 test samples. Each of these 8 items shall be tested for these requirements. If the number of defectives is found to be equal to or to exceed the rejection number corresponding to the first stage in Table 2 (that is, 2), reject the lot without further testing; otherwise proceed to the second stage.

A-2.2.5 Second Stage — In the second stage take another 8 items at random from the 40 test samples. Test them for these requirements and add the number of defectives to those found previously.

A-2.2.5.1 If the total number of defectives in the cumulative sample (8 of the first stage + 8 of the second stage, that is, 16) is found to be equal to or less than the corresponding acceptance number given in Table 2 (which is 0 for the second stage), accept the lot; if it is equal to or greater than the corresponding rejection number given in Table 2 (which is 2 for the second stage), reject the lot; if it is between the acceptance number and the rejection number, proceed to the third stage.

A-2.2.6 Third and Subsequent Stages — The procedure for the third stage and subsequent stages, if any, shall be the same as for the second stage till a decision to accept or reject the lot is reached.

IS : 4161 - 1967

(Continued from page 1)

Members

SHRI HARI DUTTA

DR S. R. LELE

SHRI J. K. WAD (Alternate)

SHRI K. V. RAMACHANDRAN

SHRI LAKHBIR SINGH

DR B. C. SINHA

Representing

The Ganga Glass Works Pvt Ltd, Balawali

Borosil Glass Works Ltd, Bombay

Ministry of Defence (R & D), New Delhi

National Physical Laboratory (CSIR), Poona

Central Glass & Ceramic Research Institute, Calcutta

Panel for Nessler Tubes, CDC 33: 1:2

Convener

DR D. N. SEN

National Chemical Laboratory (CSIR), Poona

Member

SHRI V. B. SHENOY

British Drug Houses (India) Pvt Ltd, Bombay

INDIAN STANDARDS ON Laboratory Glassware

IS:					Rs
878-1956	Graduated measuring cylinder	1.50
1117-1958	One mark pipettes	2.00
1381-1959	Boiling flasks, narrow necked	2.50
1388-1959	Reagent bottles	2.50
1541-1959	Glass filter funnels	2.00
1574-1960	Glass weighing bottles	2.00
1575-1960	Separating funnels	2.50
1590-1960	Glass filter flasks	2.50
1672-1960	Floating dairy thermometers	1.50
1915-1958	One mark graduated flask	1.50
1996-1962	Glass stopcocks	3.00
1997-1961	Burettes	3.50
2480-1964	General purpose glass thermometers	2.00
2618-1963	Test-tubes	2.00
2619-1963	Glass beakers	2.30
2620-1963	Distilling flasks	2.00
2626-1963	Petri dishes	2.00
2627-1963	Glossary of terms relating to liquid-in-glass thermometers	1.00
3055-1965	Clinical thermometers	3.00
3104-1965	Density hydrometers	4.50
5608-1966	Glass alcoholometers	2.50
4161-1967	Nessler cylinders	2.50
*4162-1967	Graduated pipettes	

*Under print.

PUBLICATIONS OF INDIAN STANDARDS INSTITUTION

INDIAN STANDARDS

Over 4 000 Indian Standards, broadly classified under the following main heads, have been issued so far:

Agriculture & Food
Chemical
Civil Engineering
Consumer Products

Electrotechnical
Mechanical Engineering
Structural & Metals
Textile

Of these, the standards belonging to the Chemical Group fall under the following categories:

Acids
 Adhesives
 Alcohols and Allied Products
 Alkalis
 Brushware
 Ceramicware, Enamelware and Laboratory Porcelain
 Chemical Hazards
 Chemicals, Inorganic (Miscellaneous)
 Chemicals, Organic (Miscellaneous)
 Coal and Coke
 Coal Carbonization Products
 Cosmetics and Toilet Goods
 Dye Intermediates
 Electroplating Chemicals
 Explosives and Pyrotechnic Materials
 Fertilizers
 Footwear
 Glass and Glassware
 Industrial Gases
 Inks and Allied Products
 KATTHA, Vegetable Tans and Allied Products

Laboratory Glassware, Thermometers and Related Apparatus
 Lac and Lac Products
 Leather, Leather Goods and Leather Dressings
 Linters and Allied Products
 Lubricants and Related Products
 Metal Containers and Closures
 Oils & Fats, Oleaginous Seeds and Fruits
 Paints and Allied Materials
 Paper, Paper Products and Packaging Materials
 Perfumery Materials, Natural and Synthetic
 Petroleum and Petroleum Products
 Petroleum Measurements
 Photographic Chemicals
 Plastics
 Polishes
 Printing Inks
 Rubber and Rubber Products
 Soaps and Other Surface Active Agents
 Thermal insulation Materials
 Treated Fabrics
 Water and Water Treatment

OTHER PUBLICATIONS

			Rs
ISI Bulletin (Published Every Month)			
Single Copy	2.00
Annual Subscription	15.00
Annual Reports (from 1943-49 Onwards)	2.00 to 3.00 each
Handbook of ISI Publications, 1966	5.00

Available from

INDIAN STANDARDS INSTITUTION

Headquarters

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 1

Telephones 27 36 11-20

Telegrams Manaksanstha

<i>Branch</i>	<i>Offices</i>	
Telegrams	Manaksanstha	
534 Sardar Vallabhbhai Patel Road	Bombay 7	Telephone 35 70 27
5 Chowringhee Approach	Calcutta 13	23-18 23
117/418 B Sarvodaya Nagar	Kanpur	3 76 95
54 General Patters Road	Madras 2	8 72 78

Printed at Delhi Printers, Delhi-6, India